

Intentions, perfect. It began in customer needs, and finally customer satisfaction!

Quality - is to get the trust of weight is the key to winning the competition, is the starting point for endless most demand, value and dignity.

Related Design

Hardness value table

HRC	HS	HV	Brandt		HRC	HS	HV	Brandt	
			HBS (30D ²)	d/mm (10/3000)				HBS (30D ²)	d/mm (10/3000)
70		1037	-	-	40	53.5	377	370	3.17
69		997	-	-	39	52.3	367	360	3.21
68	96.6	959	-	-	38	51.1	357	350	3.26
67	94.6	923	-	-	37	50	347	341	3.30
66	92.6	889	-	-	36	48.8	338	332	3.34
65	90.5	856	-	-	35	47.8	329	323	3.39
64	88.4	825	-	-	34	46.6	320	314	3.43
63	86.5	795	-	-	33	45.6	312	306	3.48
62	84.5	766	-	-	32	44.5	304	298	3.52
61	83.1	739	-	-	31	43.5	296	291	3.56
60	81.4	713	-	-	30	42.5	289	283	3.61
59	79.7	688	-	-	29	41.6	281	276	3.65
58	78.1	664	-	-	28	40.6	274	269	3.70
57	76.5	642	-	-	27	39.7	268	263	3.74
56	74.9	620	-	-	26	38.8	261	257	3.78
55	73.5	599	-	-	25	37.9	255	251	3.83
54	71.9	579	-	-	24	37	249	245	3.87
53	69.1	561	-	-	23	36.3	243	240	3.91
52	67.7	543	-	-	22	35.5	237	234	3.95
51	66.3	525	501	2.73	21	34.7	231	229	4.00
50	65.5	509	488	2.77	20	34	226	225	4.03
49	63.7	493	474	2.81	19	33.2	221	220	4.07
48	62.6	478	461	2.85	18	32.6	216	216	4.11
47	61059.7	463	449	2.89	17	31.9	211	211	4.15
46	57.1	449	436	2.93	16	-	-	-	-
45	55.9	436	424	2.97	15	-	-	-	-
44	58.4	413	413	3.01	14	-	-	-	-
43	57.1	401	401	3.05	13	-	-	-	-
42	55.9	391	391	3.09	12	-	-	-	-
41	54.7	388	380	3.13	11	-	-	-	-