





Chemical Composition mass/%									
Cu	Sn	Al	Fe	Mn	Ni	Pb	Si	P	Zn
70.0-78.0	4.0-6.0	ě	0.25	0.2	0.5-2.5	18.0-23.0	0.01	0.1	2

Mechanical properties								
Tensile strength Mpa(Min)	Yield strength MPa(Min)	Elongation %	Brinell hardness(HB)					
180	90	7	50					

## Casting Copper Alloy



